

EFFECT OF FLY ASH AND COPPER SLAG ON MECHANICAL PROPERTIES OF CONCRETE

DR. R.R. SINGH

Professor & Head, Department of Civil Engineering
Punjab Engineering College (Deemed To Be University), Chandigarh, India
rrs837angwlm@gmail.com, rrsingh@pec.ac.in

MISS. AASTHA

Ph.D. Student, Civil Engineering Department,
Punjab Engineering College (Deemed To Be University), Chandigarh, India aastha.civ@gmail.com

ABSTRACT

The present study aims at developing the concrete mixes incorporating fly ash and copper slag as a partial replacement of cement and fine aggregates respectively. The aim is to study the mechanical properties of modified concrete with fly ash and copper slag and to compare it with reference mix i.e without any supplementary material. Cement was partially replaced by fly ash with 20%, 30%, 40% replacement, and fine aggregate was partially replaced by copper slag with 30%, 40%, 50% replacement. The design mix was worked out as per Indian standard guidelines and various trials were performed to obtain the mix of grade M-25 at 28 days. In this study, the compressive strength, split tensile strength and flexural strength of concrete mixes for different percentage of replacement of cement and fine aggregate are obtained at 7 days and 28 days. After analysis of test results, it was found that performance of binary mix with fly ash was less than that of reference mix whereas performance of binary mix with copper slag was higher than that of reference mix. Results of ternary mix with both fly ash and copper slag was found to be better than that of reference mix. Cube compressive strength of mixes showed up to 27% increase in strength, split tensile strength showed up to 50% increase in strength, flexural strength showed up to 20% increase in strength. Maximum increase in compressive strength, split tensile strength and flexural strength was found for the M10 mix i.e. mix with 30% fly ash and 40% copper slag.

KEYWORDS: mechanical properties of concrete fly ash and copper slag.

1. INTRODUCTION

Concrete's use in the modern world has become an important agenda. On the other hand, recycling waste solid materials is one of the most challenging problems worldwide with the unprecedented growth of the world population and in order to combat the scarcity of cement and the increase in cost of concrete under these circumstances the use of recycled solid wastes, agricultural wastes, and industrial by products like used copper slag, fly ash, blast furnace slag, silica, rice husk, came into use. The high percentage of fly ash content in the Indian coal has resulted in huge production of fly ash at these coal-based stations. Indian Copper companies - Sterlite Industries, Hindalco, and Hindustan have contributed to the production of major quantities of copper. It is the waste product of copper from Sterlite Industries India Ltd, Tuticorin. The safe disposal of this waste is a lack, costly and causes environmental pollution.

2. EXPERIMENTAL PROGRAMME

The experimental program was planned to investigate the compressive strength, split tensile strength and flexural strength of partial replacing cement with fly ash and fine aggregating with copper slag. It also discusses the various tests conducted on copper slag and fly ash modified concrete in its hardened state. It includes tests conducted on various constituent's materials such as coarse aggregates, fine aggregates and cement. Physical properties of cement which were studied include fineness, specific gravity, consistency, initial and final setting, soundness and compressive strength. The physical properties of fine and coarse aggregates which were studied include specific gravity, grading, water absorption, sieve analysis and bulk density. Control mix of M-25 was designed as per the guidelines of IS 10262: 2009. In this study, the

influence of combination of Fly Ash and Copper Slag on the mechanical properties of concrete are presented. Concrete mixes were made with 0%,20%, 30% and 40% replacement of cement with fly ash and fine aggregate is replaced by Copper Slag with 0%,30%,40%,50% replacement keeping same water binder ratio. Further ternary mix containing fly ash and copper slag were prepared in varying percentages. On the hardened concrete various strength tests such as compressive strength (7, 28 days), split tensile strength (7,28 days) and flexural strength (7,28 days) were determined. Aim of this experiment is to compare the properties of concrete mixed with and without fly ash and copper slag used as a replacement of cement and fine aggregate respectively.

mix designation	% replacement of	% replacement of 2	Cement	Fly ash	Water	Fine aggregate (kg)	Coarse aggregate (kg)
M0	0	0	360	0	172.8	660	1265
M1	20	30	288	72	172.8	462	1265
M2	30	30	252	108	172.8	462	1265
M3	40	30	216	144	172.8	462	1265
M4	20	40	288	72	172.8	396	1265
M5	30	40	252	108	172.8	396	1265
M6	40	40	216	144	172.8	396	1265
M7	20	50	288	72	172.8	330	1265
M8	30	50	252	108	172.8	330	1265
M9	40	50	216	144	172.8	330	1265

3. MIXING, BATCHING, CASTING and CURING OF SPECIMENS

The material was weighted in batches in required proportions and was put into the mixer. The required quantity of water was added slowly to get a uniform mix. All the moulds were cleaned and were applied with oil on the inner faces well before concreting operation for casting of specimen so that oil may not affect concrete ingredients. These were securely tightened to correct dimensions before casting. Care. The complete procedures were adopted in the making and casting operations. The quantities of cement, coarse aggregates, fine aggregate, copper slag, fly ash and water for each batch was weighed accurately.

The aggregates and copper slag were put into the mixer and over that cement and fly ash were added, mixer started to rotate to mix the dry ingredients. Then water was added carefully and mixer was started to rotate, until the concrete appeared to be homogenous and of the desired consistency. The prepared concrete was then out from rotating drum into M.S. Plate. Then concrete was filled into the previously prepared moulds in three layers. Electric vibrator was used for compaction of concrete. Vibrations were stopped as soon as cement slurry appeared on the top surface of the mould. The surface of the concrete was finished level with the top of the mould using a trowel and marked properly to indicate the mix proportions date of casting. The finished specimens were left to harden. The specimens were removed from the moulds after 24 hours of casting and were placed in the water tank filled with the potable tap water in the laboratory for curing. For plain cement concrete specimens, no fly ash and copper slag were added to the mix and all the specimens for a particular testing age were cast in one batch. The specimens for fly ash concrete replacing cement by fly ash and incorporating copper slag with varying percentages of fly ash and copper slag were cast in separate batches. This procedure was adopted to ensure uniform properties of the specimens in each batch.

4. ANALYSES OF RESULTS

Table 2 Test results of compressive strength, split tensile strength and flexural strength

Mix designation	compressive strength		split tensile strength		flexural strength	
	7days	28days	7 days	28 days	7 days	28days
M0	21	33.48	2.05	3.336	4.7	5.2
M1	21.29	33.48	2.21	2.97	4.6	5.3
M2	20.8	33.9	2.42	3.5	4.4	5.3
M3	20.2	34.1	2.32	3.3	4.2	5
M4	23.82	38.44	2.7	4.03	4.9	5.7
M5	22.14	40.11	3.08	4.1	5.1	6
M6	21.28	39.44	3.01	3.9	4.6	5.6
M7	22.02	36.9	2.33	3.94	4.7	5.5
M8	21.2	35.36	2.21	3.75	4.9	5.4
M9	19.11	32.78	1.95	3.35	4.5	5.4

4.1 Compressive strength

The ternary mixes were prepared using fly ash and copper slag and their Compressive strength tests were conducted at 7 and 28 days curing periods for all mix proportions by using Compression testing machine. It can be seen from Table 2 that at 7 days compressive strength of ternary mixes containing fly ash and copper slag were more than that of the reference mix. The compressive strength has increased with increase in dosage of copper slag also depending on dosage of fly ash. The compressive strength at 28 days of ternary mixes was also more than that of reference mix. It can be seen that the use of copper slag with fly ash enhances the strength of fly ash mix concrete. This is because Combination of both industrial wastes fly ash and copper slag reacts with cement and produce binding properties to the concrete hence; it has not affected the strength at early age to later age.

4.2 Split tensile strength

The ternary mixes were prepared using fly ash and copper slag and their Split Tensile strength tests were conducted at 7 and 28 days curing periods for all mix proportions by using Compression testing machine. It can be seen from Tables 2 that at 7 days compressive strength of ternary mixes containing fly ash and copper slag were more than that of the reference mix without fly ash and copper slag for all replacement levels. The split tensile strength has increased with increase in dosage of copper slag also depending on dosage of fly ash. The split tensile strength at 28 days of ternary mixes was also more than that of reference mix and binary mixes with fly ash for all replacement levels.

4.3 Flexural strength

The ternary mixes were prepared using fly ash and copper slag and their Flexural strength tests were conducted at 7 and 28 days curing periods for all mix proportions. It can be seen from above tables and figures that at 7 days flexural strength of ternary mixes containing fly ash and copper slag were more than that of the reference mix. The Flexural strength has increased with increase in dosage of copper slag also depending on dosage of fly ash. The flexural strength at 28 days of ternary mixes was also more than that of reference mix and binary mixes with fly ash for all replacement levels. It can be seen that the use of copper slag with fly ash enhances the strength of fly ash mix concrete. The increase in strength is observed because of combination of both industrial wastes copper slag and fly ash reacts with cement and produce binding properties to the concrete hence; it has not affected the strength at early age to later age. From this study, it is concluded that flexural strength of concrete with fly ash and copper slag was always higher than control concrete. It is also suggested that, concrete with 30% fly ash replacement for cement and 40% copper slag replacement for fine aggregate is suitable for concrete structures.

5. CONCLUSIONS

The present study was undertaken to investigate the influence of fly ash and copper slag on Compressive strength, Split Tensile strength, Flexural strength The effect of fly ash and copper slag on mechanical properties of concrete proportioned with cement replacement (20%, 30%, 40%) with fly ash and fine aggregate replacement (30%, 40%, 50%) with copper slag were studied. The reference mix of M-25 grade was prepared without addition of fly ash and copper slag and the results were compared with them. Different specimens of cube, cylinder and beam were tested for compressive strength, split tensile strength and flexural strength at the age of 7 days and 28 days. Based on the results and within the scope of research the following conclusions can be drawn:

1. The ternary mix containing both fly ash and copper slag exhibited higher compressive strength as compared to binary and reference mix. At 7 days, compressive strength of mix with 20% fly ash and 40% copper slag was found to be highest. However, the mix with 30% fly ash and 40% copper slag shows a maximum increase in compressive strength at 28 days.
2. The ternary mix containing both fly ash and copper slag exhibited higher Split tensile strength as compared to binary and reference mix. The Split tensile strength of mix with 30% fly ash and 40% copper slag found to be highest both at 7 days and 28 days.
3. The ternary mix containing both fly ash and copper slag exhibited higher flexural strength as compared to binary mixes and reference mix. The split tensile strength of mix with 30% fly ash and 40% copper slag

found to be highest both at 7 days and 28 days. But the rate of increase is less as compared to split and compressive strength.

4. The mix which showed strength gain in all mechanical properties was mix M5.

REFERENCES

- I. Al-Jabri S. Khalifa, Al-Saidy H. Abdullah, Taha Ramzi (2011), "Effect of copper slag as a fine aggregate on the properties of cement mortars and concrete." *Construction and Building Materials*, Vol. 25, pp. 933–938.
- II. Ambily P.S., Umarani C., Ravisankar K., Prem Ranjan Prabhat, Bharatkumar B.H., Iyer R. Nagesh (2015), "Studies on ultra-high performance concrete incorporating copper slag as fine aggregate" *Construction and Building Materials*, Vol. 77, pp. 233–240.
- III. IS 10262: 2009, Concrete Mix proportioning – Guidelines. Bureau of Indian Standards, New Delhi. Lam, L., Wong, Y.L. and Poon, C.S., 1998. Effect of fly ash and silica fume on compressive and fracture behaviors of concrete. *Cement and Concrete research*, 28(2), pp.271-283.
- IV. Sales A.T.C., Dos Anjos M.A.G., Andrade N (2017), "Blasted copper slag as fine aggregate in Portland cement concrete" *Journal of Environmental Management*, Vol. 196, pp. 607-613.
- V. Wu Wei, Zhang Weide, Ma Guowei (2010) "Optimum content of copper slag as a fine aggregate in high strength concrete." *Materials and Design*, Vol. 31, pp. 2878–2883